

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in the application:

LISTING OF CLAIMS:

1. (currently amended): A solution casting method for producing a polymer film from a dope solution containing a polymer and a solvent, comprising steps of:

determining as a criterion measure a weight percentage of a remaining solvent in a gel-like film used to ~~product~~ produce a final product film when a peeling force for peeling said gel-like film from a substrate is at the maximum, wherein said gel-like film used to produce a final product film is formed by casting said dope solution from a casting die on the substrate;

casting said dope solution from said casting die on said substrate to form said gel-like film used to produce a final product film;

drawing said gel-like film used to produce a final product film in a tangential direction of said substrate to peel said gel-like film used to produce a final product film from said substrate at a peeling speed of at least 10 m/min;

regulating to less than 20 mm a movement range in which a peeling position of said gel-like film used to produce a final product film moves on said substrate; and

drying said peeled gel-like film used to produce a final product film so as to obtain said polymer film;

wherein a peeling roller is used for peeling said gel-like film used to produce a final product film;

wherein while said gel-like film used to produce a final product film is peeled, said weight percentage of said remaining solvent is in the range of:

5 wt.% to (said criterion measure – 5 wt.%);

wherein the criterion measure is in the range of 15 wt.% to 35 wt.%;

wherein a thickness of said polymer film is at most 60 μm , and

wherein said polymer film is a cellulose triacetate film.

2. (original): A solution casting method as claimed in claim 1, wherein the moving direction of said peeling position changes at least four times in one second along a transporting direction of said substrate.

3. (canceled).

4. (original): A solution casting method as claimed in claim 1, wherein a length of an internal common tangent of said peeling roller and said substrate is in the range of 0.1 mm to 100 mm.

5. (original): A solution casting method as claimed in claim 1, wherein a temperature of said substrate is adjusted in the range of 10 $^{\circ}\text{C}$ to 40 $^{\circ}\text{C}$.

6. (original): A solution casting method as claimed in claim 5, wherein said peeling speed is at most 150 m/min.

7. (previously presented): A solution casting method as claimed in claim 6, wherein a transporting time for transporting said gel-like film used to produce a final product film on said substrate is in the range of 0.5 min to 10 min.

8. (previously presented): A solution casting method as claimed in claim 7, wherein a temperature of said gel-like film used to produce a final product film at peeling is in the range of 10 °C to 50 °C .

9. (canceled).

10. (canceled).

11. (canceled).

12. (canceled).

13. (previously presented): A solution casting method as claimed in claim 1, wherein a peeling roller used for peeling said gel-like film used to produce a final product film is disposed downstream from said substrate, and a distance from said peeling position and said peeling roller is in the range of 0.1 mm to 100 mm.

14. (previously presented): A solution casting method as claimed in claim 1, wherein a release agent is added to said dope solution.

15. (previously presented): A solution casting method as claimed in claim 1, wherein said solvent is a mixture solvent containing dichloromethane and alcohol, and a weight ratio of said alcohol is more than 8 wt.%.

16. (previously presented): A solution casting method as claimed in claim 15, wherein at least one of methanol, ethanol, and n-butanol is used as said alcohol.

17. (previously presented): A solution casting method as claimed in claim 15, wherein materials which are acids or materials showing characters or properties of acid are in said dope solution.

18. (currently amended): A solution casting method as claimed in claim 1, wherein ~~cellulose acylate is used as said polymer~~ the cellulose triacetate film comprises cellulose triacetate having a degree of acetylation in the range of 59.0%-62.5%.

19. (canceled).

20. (canceled).

21. (canceled).